

**Execution:** white-heart malleable cast-iron - according to UNI-ISO 5922 / DIN 1592 - W40-05 quality grade according to ISO 49 / DIN 2950 - ISO 1460 warm immersion galvanizing - inside and outside threading according to ISO 7/1 and ISO 7/2 normatives.

**Diameters:** 1/4" ÷ 4"

**Pressures and temperatures:**

**Temperature**

from -20°C to +120°C

from 120°C to +300°C

300°C

**MPa max. pressure**

2.5 (25 atmospheres)

interpolated values

2.0 (20 atmospheres)

